

COLLARD & ROE, P.C.**PATENT, TRADEMARK & COPYRIGHT ATTORNEYS**

1077 Northern Boulevard

Roslyn, New York 11576

(516) 365-9802

FAX (516) 365-9805

FACSIMILE TRANSMISSION**RECEIVED**
APR 29 2003
GROUP 1700

DATE: April 24, 2003

NO. OF PAGES INCLUDING COVER PAGE: 10

TO: Examiner E.A. Bolden

FAX NO.: 1-703-872 9310

FROM: COLLARD & ROE, P.C.

RE: U.S. SER. NO. 10/059,833

Group: 1755

Applicants: T. Murata et al

FAX RECEIVED
APR 24 2003
TECHNOLOGY CENTER 2800**If you do not receive all of the pages, please call the above phone number as soon as possible.**

MESSAGE:

Dear Sir:

Enclosed please find a Response to the Office action of January 28, 2003. Please confirm receipt.

Respectfully submitted,



Kurt Kelman

KK:im

R:\USERS\jmitendorf\Kelman\FAX transmittal PTO.Miwa.wpd

message is intended only for the use of the addressee, and may contain material which is privileged and confidential. If you are not the intended recipient, dissemination of this communication is strictly prohibited. If you have received this transmission in error, please notify us immediately by telephone. Thank you.

PATENTIN THE UNITED STATES PATENT AND TRADEMARK OFFICE

4/1a
4/30/03
RECEIVED
APR 29 2003
GROUP 1700

APPLICANTS: TAKASHI MURATA ET AL EXAMINER: E.A. Bolden
SERIAL NO.: 10/059,833 GROUP: 1755
FILED: JANUARY 30, 2002
FOR: ALKALI-FREE GLASS AND GLASS PLATE FOR A DISPLAY

AMENDMENT AFTER FIRST OFFICE ACTIONBOX NON-FEE AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

FAX RECEIVED

APR 24 2003

TECHNOLOGY CENTER 2800

Sir:

In response to the Office letter of January 28, 2003,
please amend the above-identified application as follows:

IN THE CLAIMS:

Amend claims 1, 10 and 14 to read as follows:--

ai
1 (amended). 1. An alkali-free glass consisting essentially of, in mass percent, 58-70% SiO₂, 10-19% Al₂O₃, 6.5-15% B₂O₃, 0-2% MgO, 3-12% CaO, 0.1-2% BaO, 0-4% SrO, 0.1-6% BaO+SrO, 0-5% ZnO, 5-12% MgO+CaO+BaO+SrO+ZnO, 0-5% ZrO₂, 0-5% TiO₂, and 0-5% P₂O₅, containing substantially no alkali metal oxide, and having a density of 2.40g/cm³ or less, an average